

ILAC-I.S.O. Certified Third Party Test Report

DATE: October 1, 2009 **FILE:** VALUEV.A092309A
CLIENT: Creative Energies, Inc.
 1607 North Magnolia Avenue
 Ocala, FL 34475

SAMPLE IDENTIFIED BY CLIENT AS:

Vinyl Submitted
Style #: FLR10
Color White

TEST PROCEDURE:

TEST RESULTS:


FIRE RESISTANCE-STATE OF CALIFORNIA (NATURALS/SYNTHETICS) (SMALL SCALE TEST)

<u>AFTERFLAME</u>		<u>CHAR LENGTH</u>	
<u>WARP</u>	<u>FILLING</u>	<u>WARP</u>	<u>FILLING</u>
0.0 Seconds	0.0 Seconds	5.5 Inches	5.0 Inches
0.0 Seconds	0.0 Seconds	5.3 Inches	4.8 Inches
0.0 Seconds	0.0 Seconds	4.2 Inches	5.3 Inches
0.0 Seconds	0.0 Seconds	5.1 Inches	4.2 Inches
0.0 Seconds	0.0 Seconds	5.3 Inches	4.6 Inches
AVERAGE: 0.0 Seconds	0.0 Seconds	5.1 Inches	4.8 Inches

RESULT: The fabric sample submitted for testing **DOES** meet the general requirements when tested in accordance with the procedure outlined in Specification for Flame-Retardant Chemicals, Fabrics and Application Concerns, California Administrative Code Title 19 (Interior Chemicals), Section 1237.1 Small Scale Test (1993 Proposed Revision).

REQUIREMENTS: Afterflame shall not exceed 4.0 seconds for average.
 Char length shall not exceed 6.0 inches for any one specimen.

OBSERVATIONS: Afterglow: No
 Localize Burning: Yes

Signed For The Company By

 Adam R. Varley
 Technical Director
 TT/09/388




 Stacy Sadowy
 Quality Assurance Supervisor